



## TECHNICAL DATA SHEET



### DESCRIPTION

Fine body filler easy to work, characterized by good shaping properties in any required thickness. Suitable hardness of putty to hardness of paintwork and the smooth non-porous surface allows to use this product as filling and finishing putty. Easy to work also with homogenous surfaces even by applying thick coats.

**NOTE\*** Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C

### SURFACES

Fill putty was designed for use on steel and glass-fibre reinforced plastics.


### TECHNICAL DATA

**VOC:** 2004/42/IIIB(b)(250) <250

### PREPARATION AND RECOMMENDED APPLICATION



**Surface preparation:** The surface must be sanded, clean, degreased and dry.



**Mixing ratio:**

Filler	100 g
Paste hardener	2-3 g



**Application medium:** Spatula application.

**\*Recommended spatulas for application:**

- 2004-001720 KIT 4 METALLIC SPATULAS
- 2004-001540 WHITE RUBBER SPATULA
- 2004-001620 KIT 5 PLASTIC SPATULAS



**Air drying:** 16-30 min.



**Recommended sanding sheets:**

P100-P320

## CLEANING OF TOOLS

With cleaning solvent.

- 2004-001700 SPATULA CLEANER
- 2004-001701 STAR BRITE FOR SPATULA CLEANER

## SECURITY INFORMATION

See Safety Data Sheet.

## WARNING

Do not use the product at temperatures below 5°C.

Store in a cool, dry place.

*\* The theoretical yield does not contemplate the relative loss of the application.*

## CONTINUATION OF APPLICATION

Use:

- Easy Filler 4000 (Light Grey, Dark Grey, White and Black).
- HS Filler 540 (White, Grey and Black).

**AVAILABLE PACKAGING**

Code	Description	Packaging
5001-001096	FILL UNIVERSAL SOFT	500GR

\*For more information about our products or means of application, please visit our website [www.carrepairsystem.eu](http://www.carrepairsystem.eu) or send us an e-mail to [info@carrepairsystem.eu](mailto:info@carrepairsystem.eu)

*The technical information and instructions provided in this sheet are based on our own working experience. The company ensures the quality of the product. However, as the uses terms and conditions are out of our control, we decline any responsibility as the final result is concerned.*